



Improves the strength of CFRP composites due to better particle adhesion

Aniket V Renavikar¹, Dr. Akshit Lamba²

¹ Research Scholar, Department of Civil Engineering, Kalinga University, New Raipur, Chhattisgarh, India

² Guide, Department of Civil Engineering, Kalinga University, New Raipur, Chhattisgarh, India

Abstract

Because of its strength-to-weight ratio, resistance to corrosion, and design flexibility, carbon fiber reinforced polymers, or CFRP, have completely changed structural engineering in the automobile, civil infrastructure, and aviation industries. Conventional analytical approaches generally underestimate CFRP's complicated anisotropic behavior, interfacial phenomena, and damage progression processes. Advanced computer modeling, multiscale analysis, and experimental methods allow CFRP structure optimization with remarkable accuracy and dependability. The research examines how these factors affect delamination factor, surface roughness, thrust force, and mechanical qualities including tensile and flexural strength. The research seeks ideal machining settings to reduce CFRP composite drilling flaws and increase quality.

Keywords: Strength, CFRP, Composites, Weight, CFRP composites

Introduction

In recent years, CFRP composites made of carbon fiber and reinforced with polymers have become more popular in many fields of engineering, especially civil engineering. CFRP's exceptional mechanical properties, high resilience, and lightweight composites make them perfect for civil engineering projects. Over the last few decades, CFRP composites have seen a dramatic increase in their use in building and bridge construction, among other infrastructure projects.

Carbon fiber reinforced plastic Carbon is used to make (CFRP) composites. fiber that has been woven together and then treated with resin to make them robust and long-lasting. With its resin matrix providing protection from environmental elements including moisture and UV radiation, carbon fiber provides excellent rigidity, fatigue resistance, and tensile strength. The resultant composite is ideal for use in structural applications because to its low density has an impressive strength-to-weight ratio.

One major advantage composite material composed of carbon fiber One benefit of (CFRP) composites is their higher strength-to-weight ratio. Composites made of carbon fiber reinforced plastic (CFRP) have a much greater strength-to-weight ratio than traditional building materials like concrete and steel. Because of this, CFRP materials may make buildings that are lighter and more efficient while yet providing the same strength and durability as concrete and steel. Bridges and big structures are two examples of situations where weight plays a significant role, therefore this is quite helpful in such cases. One further perk of CFRP composites is how long they last. Composites constructed from CFRP-reinforced plastic are ideal for usage in extreme conditions since they are resistant to corrosion and environmental deterioration. Their strong fatigue resistance further ensures that they will not deteriorate during repeated loading cycles. Bridges that are susceptible to large loads and continuous movement should priorities this

Composites are made by combining many components to provide benefits like strength and weight reduction. Composites may be made using a variety of materials as constituents. They may be either contemporary materials

like synthetic fibers and polymers, or more conventional ones like wood fibers and mud matrixes. The aviation sector has discovered an application for fiber-reinforced polymers, military, and marine industries over the last century.

CFRP is a well-liked composite that is often used in the aerospace sector as well as in constructing constructions. CFRP composites are lightweight (density of 1500 kg/m³) and durable materials that are employed in many everyday gadgets. Generally speaking, CFRP composites make use of certain unique resins including vinyl ester, epoxy, and polyester. This method boosts interfacial adhesion, lowers stress concentrations, and improves overall structural efficacy. Advanced production techniques, such as 3D printing composites and automated fiber placement (AFP), are essential for achieving these designs with great accuracy and consistency.

Topology optimization is essential in the structural design of CFRPs, since it identifies the best possible allocation of materials within a given design area. This method facilitates the construction of lightweight structures while maintaining strength and rigidity. Due to the anisotropic characteristics of CFRPs, topology optimization may be used to strategically align fibers and minimize superfluous material consumption. It is especially successful in high-performance settings, such as the automotive and aerospace components, resulting in novel designs that are structurally robust and material-efficient.

Literature review

Nadeem (2010) reported the findings of an experimental investigation that was conducted on beams that were encased using CFRP, or carbon fiber reinforced plastic. The results of the tests clearly shown that under-reinforced RC beams may have their flexural strength significantly improved by using a technique that involves externally attaching carbon fiber reinforced plastic sheets to the tension face of the beams. Nevertheless, the growth was determined using the ratio of steel reinforcement. The concept of structural ductility does not have a definition that is widely acknowledged. The establishment of a reference base was necessary in order to conceptualize ductility in a

manner that is both reasonable and intelligible, and that can be applied to any and all structural materials. When it comes to defining ductility, the yield point of internal steel offers a reference point that is quite straightforward. On the other hand, the structural member's capacity to withstand load while experiencing significant deformations is a result of the distinctive yield plateau that is seen in the steel's stress-strain curve. However, No matter what kind of reinforcing material was used, this was never the case with FRP sheet bonded reinforced concrete beams. Or a steel and FRP mix. Sarah Orton and James (2009) the purpose of doing an experiment was to examine the processes that enhance the negative moment zone. By forcing hinging to take place at regions with better rotational ductility, they were able to achieve the requisite load to prevent progressive collapse. Additionally, they were able to employ a much-reduced amount a material made recycled plastic material made from carbon fiber (CFRP). The carbon fiber reinforced plastic (CFRP) needed was much higher, however the flexural strengthening scheme that was developed was successful in achieving the requisite load to withstand progressive collapse at a low degree of displacement. According to the findings, an approach that uses CFRP, or carbon fiber reinforced plastic, offers reinforcing continuity in a concrete beam has the potential to be effective, although it may or may not be adequate to restrict progressive collapse. Byong (2008) emphasized the impact that the application of epoxy mortar patch end anchorages has on the way carbon fiber-reinforced polymer (CFRP) sheets improve the flexural strength of beams made of reinforced concrete. The results of the tests show that carbon fiber reinforced plastic sheet reinforced concrete beams may be strengthened using epoxy mortar patch end anchorages to postpone or avoid early debonding failure. Consequently, this enhances the beam's flexural performance. The author demonstrated that the mortar patch anchoring that was used in the experimental investigation was extremely efficient in postponing or preventing the primary failure mechanism for beams that were traditionally strengthened with CFRP, which was premature debonding failure. Tamer El Maaddawy (2007) In corrosive environmental circumstances, the presented findings are based on an experimental study that attempted to evaluate the performance of CFRP sheets used for the restoration of reinforced concrete beams. After the correction was finished, the author realized that the beams' deflection capability decreased as the corrosion proceeded. There was an average reduction of forty-five percent in the deflection capability of comparing the restored beams to the control beam. Sing-ping Chiew (2007) provided both experimental and computational research on the way reinforced concrete beams (RCB) enhanced with glass fiber reinforced plastic (GFRP) handle flexural loads. According to the author's findings, flexural RC beams may have their tension faces reinforced using GFRP laminates, making them stronger and more rigid. So long as the axial stiffness external GFRP laminates is increased, the strengthening ratio rises in a linear fashion. When compared to the stresses induced by flexural cracking, the interfacial shear stress concentration that was caused by the cut off effect was far less significant. An unsuccessful attempt at debonding took place when the shear span's interfacial bond was used to its maximum

capacity. Because of the GFRP laminates' debonding, each and every reinforced beam was unsuccessful.

Research methodology

Material

This is due to the possibility that these materials may be produced with enhanced physical properties and increased mechanical behavior. The primary benefits that advanced composites provide include high strength/stiffness to weight ratios, which lead to a large decrease in weight, improved rigidity and damping, the flexibility to modify the characteristics to suit loading requirements, and the material's capacity to take on a nearly net shape.

Testing CFRP Plates for Tensile Strength

For the purpose of tensile testing using a Universal Testing Machine (UTM). Following the guidelines set out by ASTM, the CFRP composite plates were treated in order to create tensile specimens. The digital display that was connected to the UTM was used to take note of the load displacement diagram as well as the load displacement data. Through the use of the standard approach, this load and displacement data were converted into real stress and true strain data, and CFRP composites' final tensile strength values were derived. Figure 1 depicts the universal tensile testing machine that was used, and information on its characteristics may be found in Table 1.



Fig 1: Universal Testing Machine

Table 1: Details of the Universal Testing Machine

Model	UTE-100
Measuring capacity	1000 KN
Measuring range	0-1000 KN
Load resolution	100 N
Load range with accuracy of measurement $\pm 1.0\%$	20 to 100 KN

Tools & Specifications

These drill bits are of the solid kind and are manufactured of high-strength steel (HSS). They were employed in the ongoing research project. A two-fluted, straight-shank twist drill bit with a 100-degree point angle was used for the experiment. Degrees, 118 degrees, and 135 degrees, and a diameter of 6 millimeters was used. It was decided to acquire the conventional drill tool that has a point angle of 118 degrees.

Experimental Design

For the purpose of accomplishing the aim, the primary cutting parameters that spindle a thorough analysis was conducted on the variables speed (V), point angle (θ), and

feed rate (f), all of which have a substantial impact on the drilling of CFRP composites, into determine the impact they have on performance.

To identify the ideal spindle velocity, feed rate, and point angle combinations, the first trial trials were conducted. To use HSS to drill CFRP composites twist drill bits, Taguchi's L27 (3^{13}), which is an orthogonal array, was used. 13 columns are included in this array, which defines 27 different experimental runs. As shown in Table 2, the parameters were assigned to the L27 columns in order to prevent aliasing and interactions with the primary parameters. On the basis of a linear graph, the input drilling parameters are allocated to the columns (1, 2, and 5) of the orthogonal array.

Table 2: Designing an experiment using the L27 orthogonal array

Experimental Run	1	2	3	4	5	6	7	8	9	10	11	12	13
1	1	1	1	1	1	1	1	1	1	1	1	1	1
2	1	1	1	1	2	2	2	2	2	2	2	2	2
3	1	1	1	1	3	3	3	3	3	3	3	3	3
4	1	2	2	2	1	1	1	2	2	2	3	2	3
5	1	2	2	2	2	2	2	3	3	3	1	3	1
6	1	2	2	2	3	3	3	1	1	1	2	1	2
7	1	3	3	3	1	1	1	3	3	3	2	3	2
8	1	3	3	3	2	2	2	1	1	1	3	1	3
9	1	3	3	3	3	3	3	2	2	2	1	2	1
10	2	1	2	3	1	2	3	1	2	3	1	3	1
11	2	1	2	3	2	3	1	2	3	1	2	1	2
12	2	1	2	3	3	1	2	3	1	2	3	2	3
13	2	2	3	1	1	2	3	2	3	1	3	1	3
14	2	2	3	1	2	3	1	3	1	2	1	2	1
15	2	2	3	1	3	1	2	1	2	3	2	3	2
16	2	3	1	2	1	2	3	3	1	2	2	2	2
17	2	3	1	2	2	3	1	1	2	3	3	3	3
18	2	3	1	2	3	1	2	2	3	1	1	1	1
19	3	1	3	2	1	3	2	1	3	2	1	2	1
20	3	1	3	2	2	1	3	2	1	3	2	3	2
21	3	1	3	2	3	2	1	3	2	1	3	1	3
22	3	2	1	3	1	3	2	2	1	3	3	3	3
23	3	2	1	3	2	1	3	3	2	1	1	1	1
24	3	2	1	3	3	2	1	1	3	2	2	2	2
25	3	3	2	1	1	3	2	3	2	1	2	1	2
26	3	3	2	1	2	1	3	1	3	2	3	2	3
27	3	3	2	1	3	2	1	2	1	3	1	3	1

Data analysis

In the course of this research project, CFRP composite plates were manufactured by means of a manual lay-up approach. Using a computer numerical control (CNC)

machine, we conducted drilling trials with varying degrees of variation in the drilling process parameters. Among these considerations were the feed rate, point angle, and spindle speed. The results of the literature study show that the tool

parameter significantly affects the quality of the holes produced. We chose three different degrees of spindle speed, point angle, and feed rate to conduct testing inside Taguchi's L27 orthogonal array architecture. For each experiment, we ran it three times and took the mean for further examination.

Test on Tensile

Following specimen preparation and procedure execution, tensile tests were conducted in compliance with the ASTM D638 standard. The Universal Testing Machine (UTM) guided the execution of the tensile tests. Next, the specimen has to be placed within the UTM. Then, the tensile stress needs to be applied until the specimen breaks.

Figure 2 displays the results of the tensile testing of CFRP composites. After reaching a particular concentration, the tensile strength of the epoxy matrix decreases due to nano-particle agglomeration, while it initially rises with increasing weight percent of alumina nanoparticles.

Table 3: Tensile strength variation as the weight percentage of Al₂O₃ increases

Material Composition	Tensile Stress (MPa)
CFRP (0% Al ₂ O ₃)	525
CFRP (2% Al ₂ O ₃)	560
CFRP (4% Al ₂ O ₃)	540




Fig 2: Tensile strength variation as the weight percentage of Al₂O₃ increases

Test on Flexural Strength

The greatest tensile stress that a composite material is able to sustain while bending before it reaches its breaking point is referred to as its flexural strength. Figure 3 depicts the testing equipment that is used for CFRP composite samples undergo the three-point bend test as per the standard test protocol outlined in ASTM D790. For the purpose of determining the flexural strength, each test is carried out three times for each various kind of composite, and the average result is included into Equation (4.9).

Due to high adhesion at the interface of the fiber and the matrix for Al₂O₃ distributed CFRP composites, which are already impacted by the residual stress of the matrix on the fiber surfaces, it was shown that the flexural strength of CFRP composites increases with increasing weight percent of Al₂O₃.

$$\text{FlexuralStrength}=\frac{3PL}{2bt^2} \tag{4.9}$$



Fig 3: Setting up for flexural testing

Table 4: Flexural strength variation as the weight percentage of Al₂O₃ increases

Material Composition	Flexural Stress (MPa)
CFRP (0% Al ₂ O ₃)	135
CFRP (2% Al ₂ O ₃)	175
CFRP (4% Al ₂ O ₃)	145



Fig 4: Flexural strength variation as the weight percentage of Al₂O₃ increases

Results of flexural testing performed on CFRP composites are shown in Figure 4. It is evident that as the weight percent of Al₂O₃ in the epoxy matrix increases, up to a concentration of 2%, the flexural strength of the epoxy matrix also rises. But when the epoxy matrix contains 4 weight percent Al₂O₃, the flexural strength drops because nanoparticles clump together. According to the findings of the tests, the CFRP composite material that contains 2% Al₂O₃ has the highest flexural strength on the market when compared to other compositions. As a result of the Al₂O₃ nanoparticles being distributed evenly throughout the epoxy matrix, the flexural strength was significantly improved. At larger concentrations, aggregations of the Al₂O₃ nanoparticles take place, which results in a reduction in the composites' flexural strength.

Optimizing the parameters of the drilling process

When it comes to practically all industrial sectors, the optimization of machining processes is essential in order to provide prompt solutions to the rapidly shifting needs of end users. It is essential that the ratio of costs to quality of goods throughout the production stage be meticulously monitored, and immediate corrective steps must be done in the event that there are deviations from the desired output. There is an increase in the complexity of machining procedures when a

single element or a combination of several variables impact the process.

These factors include the material of the cutting tool and the work piece. In addition, industrial engineers have little time for production setup; hence, it is of the utmost importance to discover the ideal cutting conditions by minimizing the amount of time spent on trial and error and the amount of

money spent on the process. In this particular piece of work, the gray relational analysis is applied in order to evaluate the many performance features of the drilling process for CFRP composites.

Tables 5, show the drilling factors and performance traits of how well HSS drills work when drilling CFRP composite plates

Table 5: Results of the tests done on drilling a CFRP plate without Al₂O₃

Exp. No	Spindle Speed (V) RPM	Point angle (θ) degree	Feed (f) mm/min	Delamination factor		Surface Roughness (R _a) μm	Thrust Force (F) N
				Entry	Exit		
1	1000	100	50	1.4215	1.4302	1.50	60.018
2	1000	100	100	1.4802	1.6847	1.64	66.289
3	1000	100	150	1.5047	1.7618	1.88	79.542
4	1000	118	50	1.4795	1.6821	1.95	93.978
5	1000	118	100	1.5152	1.7753	2.07	101.582
6	1000	118	150	1.5991	1.8232	2.27	124.403
7	1000	135	50	1.4751	1.6694	2.95	93.461
8	1000	135	100	1.5257	1.8238	3.27	104.735
9	1000	135	150	1.5756	1.8765	3.54	124.259
10	2000	100	50	1.4194	1.5247	1.26	55.651
11	2000	100	100	1.4702	1.5936	1.40	61.823
12	2000	100	150	1.5006	1.7342	1.50	77.362
13	2000	118	50	1.4539	1.4857	1.64	84.352
14	2000	118	100	1.5068	1.7939	1.69	92.871
15	2000	118	150	1.5383	1.8831	1.83	108.991
16	2000	135	50	1.4597	1.4990	2.46	90.694
17	2000	135	100	1.5129	1.8480	2.79	94.144
18	2000	135	150	1.5538	1.8582	3.06	119.923
19	3000	100	50	1.4175	1.4831	1.22	50.783
20	3000	100	100	1.4672	1.5893	1.23	58.793
21	3000	100	150	1.4881	1.6941	1.40	66.548
22	3000	118	50	1.4369	1.4649	1.50	78.615
23	3000	118	100	1.4891	1.7336	1.67	76.981
24	3000	118	150	1.5288	1.8644	1.76	108.423
25	3000	135	50	1.4578	1.4921	2.00	86.428
26	3000	135	100	1.5068	1.7680	2.22	90.655
27	3000	135	150	1.5447	1.8929	2.84	113.461

Conclusion

An examination into unique techniques to structural design and analysis for A new generation of carbon fiber reinforced polymers (CFRP) has emerged, with the goal of making these high-tech composites even more efficient and effective. The goal of these improvements is to make the composite materials work better. Carbon fiber reinforced polymers (CFRPs) have found broad use due to their exceptional strength-to-weight ratio, corrosion resistance, and robust mechanical properties. Drilling studies made up the second stage. The drilling performance of CFRP composites with different compositions was investigated via experiments carried out on a CNC Vertical Milling machine. Additionally, for each of the investigated compositions, the tensile and flexural strengths of the composites were compared.

References

1. Wahab S, Suleiman M, Shabbir F, Mahmoudabadi NS, Waqas S, Herl N, *et al.* Predicting confinement effect of carbon fiber reinforced polymers on strength of concrete using metaheuristics-based artificial neural networks. *arXiv [Preprint]*. 2023; arXiv:2403.13809.
2. Wang D, Xu W, Wang Y, Gao J. Design and optimization of tapered carbon-fiber-reinforced

polymer rim for carbon/aluminum assembled wheel. *Polym Compos.* 2020;42. doi:10.1002/pc.25822

3. Wang Y, Wang F, Xu Q, Hong J, Wang D, Ye K, *et al.* Design and analysis of a novel carbon fiber reinforced polymer sandwich adhesive joint. *Appl Compos Mater.* 2023;30:1-23. doi:10.1007/s10443-023-10113-z
4. Hintze W, Hartmann D. Modeling of delamination during milling of unidirectional CFRP. *Procedia CIRP.* 2013;8:444-9.
5. Huang X. Fabrication and properties of carbon fibers. *Materials (Basel)*. 2009;2(4):2369-403. doi:10.3390/ma2042369
6. Xu Y, Gao Y, Wu C, Fang J, Sun G, Steven G, *et al.* On design of carbon fiber reinforced plastic (CFRP) laminated structure with different failure criteria. *Int J Mech Sci.* 2021;196:106251. doi:10.1016/j.ijmecsci.2020.106251
7. Ho Y, Sasayama H, Yanagimoto J. Mechanical properties and drawing process of multilayer carbon-fiber-reinforced plastic sheets with various prepreg thicknesses. *Adv Mech Eng.* 2017;9(3):1-12. doi:10.1177/1687814017692695
8. Nakagawa Y, Mori K, Maeno T. 3D printing of carbon fibre-reinforced plastic parts. *Int J Adv Manuf Technol.* 2017;91:2811-7. doi:10.1007/s00170-016-9891-7

9. Liu Z, Lei Q, Xing S. Mechanical characteristics of wood, ceramic, metal and carbon fiber-based PLA composites fabricated by FDM. *J Mater Res Technol*. 2019;8:3741-51.
10. Zeng JJ, Duan ZJ, Guo YC, Xie ZH, Li LJ. Novel fiber-reinforced polymer cross wrapping strengthening technique: a comparative study. *Adv Struct Eng*. 2019;23. doi:10.1177/1369433219884451
11. Zhang C, Zhang X, Duan Y, Xia Y, Ming Y, Zhu Y. Deformation resistance performance of carbon fiber-reinforced plastic machined by controlling drilling area temperature below the glass transition temperature. *Materials (Basel)*. 2021;14(6):1394. doi:10.3390/ma14061394. PMID: 33809383; PMCID: PMC8000319.
12. Zhang H, Chen W, Chen D, Zhang L. Assessment of the exit defects in carbon fibre-reinforced plastic plates caused by drilling. *Key Eng Mater*. 2001;196:43-52.
13. Zhang LB, Wang LJ, Liu XY. A mechanical model for predicting critical thrust forces in drilling composite laminates. *Proc Inst Mech Eng B J Eng Manuf*. 2001;215:2135-46.
14. Vijayan DS, Sivasuriyan A, Devarajan P, Stefańska A, Wodzyński Ł, Koda E. Carbon fibre-reinforced polymer (CFRP) composites in civil engineering application: a comprehensive review. *Buildings*. 2023;13(6):1509. doi:10.3390/buildings13061509